

Highland Copper Announces Updated Process Plant Flow Sheet Demonstrating Increased Copper Recoveries of 87.6% and Reduced Processing Costs

04.09.2025 | [GlobeNewswire](#)

[Highland Copper Company Inc.](#) (TSXV: HI; OTCQB: HDRSF) ("Highland" or the "Company") is pleased to announce positive results from its 2025 metallurgical test work program for the 100%-owned Copperwood Project ("Copperwood"), located in Michigan's Upper Peninsula. The test work was conducted by Base Metallurgical Laboratories Ltd. ("Base Met Labs") in Kamloops, British Columbia, with technical oversight provided by DRA Americas Inc. ("DRA").

In Q1 2025, Highland initiated a metallurgical test program with the goal of improving the process plant design, incorporating ultrafine flotation technology, and broadly reconsidering the operating cost structure of the process plant. Highland is pleased to announce the process plant has been redesigned to reflect a more effective comminution circuit, a simpler flotation circuit incorporating Jameson cell ultrafine flotation technology, and an optimized reagent scheme. This is anticipated to deliver an increase in copper recoveries to 87.6% at lower plant capital and processing costs. While more effective, the redesigned process plant is smaller in scale and requires lower overall power consumption. Highland is pleased that Glencore Technologies is prepared to offer a performance guarantee in relation to the improved copper recovery estimate, providing confidence in the robust nature of the test program and its results.

This metallurgical update is an important component of Phase 1 detailed engineering, also initiated in Q1 2025. The goal of Phase 1 engineering is to finalize design criteria related to process plant, mine, tailings, and water management. As demonstrated by the redesigned process plant, Phase 1 engineering represents a significant re-evaluation by Highland Copper's project team, overseen by Project Director, Dr. Wynand van Dyk. Dr. van Dyk has a degree in Chemical Engineering/Extractive Metallurgy and a 30-year career in mine design, construction and operations. Highland looks forward to providing further project design updates as Phase 1 engineering concludes in September 2025.

Metallurgical Test Work Highlights:

- **Comprehensive Testing Program:** Conducted 45 kinetic rougher and cleaner flotation tests to refine grind parameters and reagent schemes, along with locked-cycle tests and pilot-scale testing on ultrafine flotation technology.
- **Optimized Process Circuit:** Adopted a mill-float-mill-float ("MF2") flowsheet including a de-sliming stage prior to the secondary milling stage. The addition of a de-sliming stage ahead of the secondary milling and roughers allows for the rejection of up to 25% of the mass from the primary rougher tailings. This configuration reduces over-grinding and offers potential comminution energy savings of between 10 and 13.7%.
- **Improved Reagent Scheme:** Developed an optimized reagent suite that is expected to reduce operating costs by up to \$1.00 per tonne milled, while also improving environmental, health and safety ("EH&S") performance.
- **MF2 Circuit and Improved Reagent Scheme Performance:** Test work with the MF2 circuit and optimized reagent scheme delivered kinetic rougher copper recoveries of up to 92.4% at the target rougher concentrate grade of 4.5% copper, a notable improvement over the 89.7% baseline from 2018 test work. Kinetic cleaner circuit recoveries were maintained at levels comparable to the 2018 baseline. Importantly, locked-cycle tests confirmed up to 85.8% recovery at a 25% copper concentrate grade, demonstrating that the enhanced reagent scheme and MF2 configuration is capable to deliver meaningful operating cost savings without compromising metallurgical performance.

- **Projected Ultrafine Flotation Performance Gains:** Through the introduction of ultrafine flotation technology, the adoption of an MF2 circuit, and the implementation of an optimized reagent scheme, Copperwood is now expected to achieve average copper recovery of 87.6% at a concentrate grade of 25% copper, all at lower operating costs. Glencore Technologies is prepared to offer a process guarantee related to recovery and grade estimates. This marks a significant step-change from the 2023 Feasibility Study¹, which reported 86% recovery at 25% copper grade, underscoring the strength of the redesigned metallurgical flowsheet.

Dr Wynand van Dyk, Project Director for the Copperwood project, commented: "These results represent the culmination of a complete re-evaluation and re-engineering of the Copperwood metallurgical flowsheet. The outcome is a robust circuit design, firmly grounded in fundamental principles and tailored to the orebody itself. I want to extend my sincere thanks to both the DRA and Base Met Labs teams for their dedication and countless hours of effort throughout this test work program. Once we finalize the process design, we will be well-positioned to advance confidently into the detailed engineering phase."

Barry O'Shea, President and CEO of Highland Copper commented: "These metallurgical results represent another key milestone as we advance toward a construction decision in 2026. The outcomes support a clear pathway to lower processing costs, with projected recoveries exceeding those in our 2023 Feasibility Study. As detailed engineering progresses with DRA, we are encouraged by the potential to enhance project economics and reduce technical risk."

Next Steps:

As announced in January 2025, Highland awarded the Front-End Engineering and Design (FEED) contracts for both the mine and process plant to DRA. The 2025 metallurgical program has provided critical data to finalize process plant design criteria under Phase 1 of the engineering program. The next steps will focus on:

- **Variability Work:** Completion of lock-cycle variability testing on the finalized flowsheet. This work is expected to conclude in early Q4 2025.
- **Design Criteria Finalization:** Confirmation of the final process design criteria ahead of initiating Phase 2 of the detailed engineering program.

SUPPORTING TECHNICAL DETAIL

Sample selection and spatial context

The 2025 metallurgical drilling campaign comprised 10 PQ-size drill holes, designed to provide representative material from the early mine years for metallurgical testing. These holes were twinned at the five locations previously sampled during the 2017-2018 flotation test work campaign, which formed the basis of the 2018 comprehensive metallurgical program conducted by SGS² (see Figure 1). The sampling intervals, received sample masses, and assay values are summarized in Table 1.

To align with geotechnical recommendations for mine design, each metallurgical interval excluded the uppermost 30cm of the Lower Copper Bearing Sequence (LCBS), as per the geotechnical recommendations for the mine design. In total, 404 kg of core was collected and used to prepare the composite sample for the current phase of test work, as well as to prepare variability samples for the forthcoming lock-cycle variability testing.

One of the drill holes, CW-25-211, intersected the main Copperwood Fault, providing an additional 41.7kg of mineralized fault-repeat material (sample CW-25-211FR). As this material is a structural repeat of the LCBS, it was used in preliminary bench-scale tests to replicate the performance of the 2018 flotation program. This strategy allowed Highland to preserve the primary composite material for the broader 2025 metallurgical testing campaign.

Table 1: 2025 test work sample detail

Sample	Interval [m]		Received sample mass [kg]	Assays							
	From	To		Cu	Fe	Au	Ag	S	CuOx	CuCN	SO ₄ S ₂
CW-25-210	143.46	146.26	40.9	1.89	6.39	-	2.70	0.55	0.40	1.17	0.03 0.52

CW-25-211	142.95	145.15	34.1	1.83	6.23	-	4.17	0.51	0.41	1.17	0.04	0.48
CW-25-212	173.26	176.24	45.4	2.29	6.19	-	5.03	0.62	0.42	1.52	0.01	0.61
CW-25-213	172.82	175.80	45.4	2.20	6.09	-	4.67	0.66	0.21	1.76	0.07	0.59
CW-25-214	228.20	230.51	35.5	2.21	6.16	-	4.53	0.61	0.23	1.82	0.02	0.59
CW-25-215	227.86	230.38	38.0	2.24	6.00	-	3.00	0.58	0.24	1.74	0.02	0.57
CW-25-216	200.45	203.39	42.3	2.26	6.03	-	3.67	0.60	0.22	1.79	0.03	0.58
CW-25-217	201.14	203.92	42.3	2.42	5.92	-	4.73	0.63	0.22	1.90	0.02	0.61
CW-25-218	168.34	170.96	40.7	2.16	6.25	-	5.33	0.58	0.21	1.79	0.04	0.54
CW-25-219	167.50	170.14	39.5	2.57	6.16	-	7.33	0.66	0.22	1.98	0.05	0.60
Composite			404.0	2.14	6.04	0.02	5.70	0.61	0.20	1.95	0.04	0.53
CW-25-211FR	145.53	148.37	41.7	2.18	6.15	-	2.07	0.61	0.40	1.56	0.03	0.58

To confirm the representativeness of the 2025 composite sample, preliminary rougher bench-scale flotation tests were done. The objective of these tests was to replicate the metallurgical performance observed during the 2018 flotation program, thereby providing confidence in the validity of the new sample set.

Figure 2 presents the mass pull versus recovery curves from these preliminary tests, alongside historical data from the 2018 campaign - specifically Test F19 and Test F71. Test F19 represented the optimal rougher flotation conditions applied during the majority of the 2018 test work, while test F71 served as the baseline for a campaign which employed excessive NaHS dosages exceeding 2,600 g/t.

Figure 1: 2025 metallurgical test work sample locations corresponding with 2018 SGS metallurgical campaign.

As shown in Figure 2, the 2025 sample demonstrates a metallurgical response consistent with the 2018 baseline results. This correlation supports the representativeness of the new composite material. On this basis an additional 19 rougher and 20 cleaner kinetic flotation tests were carried out to optimize the process flowsheet and refine the reagent scheme.

Figure 2: Mass pull versus Recovery curves for preliminary rougher tests, confirming similar response to 2018 SGS baseline

Process flowsheet and reagent scheme optimization

Preliminary rougher flotation testing revealed that the Copperwood ore body contains bimodal mineralogical fractions: a fast-floating component that responds quickly to flotation and a slower-floating bulk fraction with more protracted kinetics. As shown in Figure 3, the fast-floating material generates a high-grade initial froth characterized by well-loaded bubbles (Panel A). However, after approximately 7 minutes of flotation time, froth quality deteriorates, becoming brittle and poorly loaded (Panel B). While metallurgical upgrading continues beyond this point, the recovery rate slows significantly, requiring extended flotation residence times. An assay-by-size analysis of tailings confirmed the presence of a low-grade ultrafine (sub 20mm) fraction, likely introduced through overgrinding in the previous single-stage milling setup.

Figure 3: Initial high-grade froth (panel A) and depleted brittle froth (panel B) after 7 minutes of flotation

Adoption of an MF2 circuit

To address these challenges, the flowsheet was revised to adopt a mill-float-mill-float (MF2) configuration, incorporating a de-sliming stage between the primary and secondary milling circuits (see Figure 4). This approach, widely established in metallurgical operations, helps mitigate overgrinding and the associated fines losses. Grind optimization test work determined the optimal parameters as:

- Primary circuit grind P80: 80 μm
- Secondary circuit grind P80: 38 μm

Bench-scale de-sliming was performed via wet screening at 38 μm , while later pilot-scale testing employed cyclone separation.

Figure 4: Revised front-end of the circuit showing desliming and mill-float-mill-float (MF2) configuration

De-sliming Efficiency and Mass Rejection

Test work demonstrated a strong linear relationship ($R^2 = 0.691$) between the mass fraction and copper grade in the de-slime fraction (see Figure 5). At a target grade of 0.3% Cu in the de-slime product, up to 25% of the mass of the primary rougher tailings can be rejected ahead of secondary milling. This not only reduces the size requirement for the secondary milling circuit but also prevents overgrinding and associated fine particle losses.

Figure 5: Linear relationship between deslime mass fraction and Cu grade of deslime fraction

Comminution Circuit Power Saving

The 2023 FSU contemplated an MF1 circuit comprising a 5.5 MW SAG mill and a 5.5 MW ball mill in closed circuit with cyclones, producing a flotation feed P80 of 45 μm and drawing 4.8 and 5.0 MW respectively. This configuration included a single rougher stage with 50 minutes of residence time, followed by a 2.2 MW regrind mill drawing 1.9 MW. In total, the circuit incorporated 13.2 MW of installed comminution power, with a projected power draw of 11.7 MW.

Under the new configuration, designed for a coarser primary grind target of 80 μm , DRA's mill sizing indicates that a 3.8 MW SAG mill and 3.8 MW ball mill represent the optimal setup for the primary milling circuit, with projected power draws of 3.3 MW and 3.4 MW, respectively. Following the de-slime step, a new secondary milling circuit (3.0 MW installed, 2.0 MW power draw) will deliver the secondary grind target of 38 μm . In addition, a 1.5 MW regrind mill (1.4 MW projected draw) will regrind the rougher concentrate to a target P80 of 10 μm .

Altogether, the revised comminution circuit is projected to draw just 10.1 MW, representing between 10% and 13.7% reduction in power requirements compared with the 2023 FSU design-highlighting both improved operating efficiency and the potential for meaningful cost and energy savings.

Reagent Scheme Optimization

In parallel with flowsheet improvements, the flotation reagent suite was also optimized to improve both performance and cost-efficiency (see Table 2). Key changes include:

- Replacement of SIBX collector with PAX
- Substitution of A-249 promoter with A-407
- Adjust pH and redox potential in the primary rougher conditioning stage, reducing NaHS dosage
- Elimination of Polypropylene glycol methyl ether (D-250)

● Elimination of n-Dodecyl Mercaptan (NDM)

In the 2023 FSU, flotation reagents accounted for \$6.50 per tonne milled in operating costs. The revised 2025 reagent suite is projected to reduce this cost to \$5.49 per tonne (at current reagent pricing), yielding a savings of up to \$1.00 per tonne. In addition to the cost reduction, the updated reagent scheme offers a substantially improved environmental, health, and safety (EH&S) profile.

Table 2: Reagent regimes and contribution to operating costs (updated to 2025 reagent pricing)

Reagent type	Dosage (g/t)	
	2023 Feasibility	2025 reagent suite (approximate dosages)
Sodium Isobutyl Xanthate (SIBX)	317	-
Potassium Amyl Xanthate (PAX)	-	450
A249 promotor	335	-
A407 propotor	-	265
Sodium Hydrosulphide (NaHS)	1089	550
Carboxymethyl Cellulose Sodium (CMC)	138	110
Sodium Silicate	98	330
Methyl Isobutyl Carbinol (MiBC)	33	100
Polypropylene glycol methyl ether (D-250)	75	-
n-Dodecyl Mercaptan (NDM)	89	-
Contribution to operating cost (\$/t milled)	\$6.50	\$5.49

Enhanced Rougher Recovery

Figure 6 presents the mass pull versus recovery curves from selected MF2 bench-scale flotation tests, shown alongside the 2018 campaign baselines from Test F19 and Test F71. A notable step-change is observed at approximately 20% mass pull, which reflects the transition between flotation products from the primary and secondary milling stages. Data points below the 20% mass pull correspond to the primary milling circuit and primary rougher flotation, while those above 20% represents recovery contributions from the secondary milling circuit and roughers.

Figure 6: Mass pull versus Recovery curves for MF2 bench tests compared with 2018 SGS baseline

Figure 7 presents linear grade-recovery curves fitted to the secondary rougher flotation data from both the 2018 and 2025 test programs. The fitted models yield R^2 values of 0.97 for both datasets, indicating a strong correlation between grade and recovery in the secondary rougher stage. The shaded regions represent the 95% confidence intervals for each regression line.

Figure 7: Fitted Grade-Recovery curves for 2025 MF2 rougher tests compared with 2018 SGS baseline

At the target rougher concentrate grade of 4.5% copper, the updated reagent scheme and MF2 circuit achieved a rougher recovery of up to 92.4%, compared to 89.7% in the 2018 baseline. Importantly, the non-overlapping confidence intervals confirm that this improvement is statistically significant, underscoring the technical merit of the revised flowsheet and reagent strategy.

Consistent Cleaner Recovery

Bench-scale cleaner optimisation focussed on refining reagent addition rates and evaluating the impact of regrind size on performance. Figure 8 illustrates the grade versus recovery curves from selected 2025

cleaner kinetic tests, presented alongside historical data from the 2018 campaign - specifically Test F55 and Test F73.

- Test F55 represented the best cleaner performance under conditions of natural pH and a regrind P80 of 14mm, which was applied during most of the 2018 test work.
- Test F73 served as the baseline cleaner performance incorporating stagewise NaHS dosages exceeding 2,600 g/t.

As shown in Figure 8, 2025 cleaner recoveries were comparable to or exceeded those achieved in the 2018 baseline tests, indicating strong and reliable downstream circuit performance. Notably, Test C48, conducted at a regrind P80 of 10µm using the revised 2025 reagent scheme (as detailed in Table 2), delivered cleaner performance outperforming Test F55 and comparable to Test F73.

Figure 8: Grade versus Recovery curves for 2025 cleaner kinetic tests compared with 2018 SGS baseline

Underscored by locked cycle tests

While kinetic rate flotation tests, used in the earlier rougher and cleaner optimization work, provide valuable insights, they do not account for the circulating loads that occur in an operating flotation circuit. To better approximate real operating conditions, locked-cycle tests are employed, offering a more realistic measure of recovery, grade, and concentrate mass pull.

Using the test C48 conditions as a basis-but incorporating closed-circuit cleaners-a locked-cycle test (C52) was completed, with results summarized in Table 3. For comparison, the average locked-cycle test results for the Copperwood Main Zone from the 2023 FSU (see Table 13.29) are also shown.

At a comparable copper recovery (85.4% vs. 85.8%), the locked-cycle test delivered a significant improvement in concentrate grade-32.9% Cu compared with 25.1% Cu. This shift in the grade-recovery curve is primarily attributed to a lower mass pull to concentrate (5.9% vs. 7.3%).

Table 3: Results of locked cycle test C52 using test C37 configuration and closed-circuit cleaners

Cycle	Mass pull [%]	Grade [%] (Ag = g/t)				Recovery [%]			
		Cu	Fe	Ag	S	Cu	Fe	Ag	S
A	5.5	36.2	7.3	72.3	10.5	82.9	7.5	77.2	84.9
B	3.4	45.1	7.8	88.6	13.2	77.0	4.9	65.3	80.8
C	4.7	37.3	7.9	69.5	10.7	78.9	6.6	66.7	87.0
D	6.8	29.8	7.3	56.5	8.6	85.6	8.7	75.8	88.3
E	6.0	33.2	6.6	64.0	9.7	85.0	7.1	75.4	87.4
F	5.9	32.6	6.6	61.3	9.2	85.7	7.2	74.8	89.1
Cycle E+F Average	5.9	32.9	6.6	62.5	9.4	85.4	7.1	75.1	88.3
FSU Table 13.29	7.3	25.1		61.2		85.8		78.8	

Because test C48 served as the basis for the C52 locked-cycle test, it is reasonable to conclude that the shape of the grade-recovery curve is maintained, but shifted to the right as a result of the closed cleaner circuit. The grade-recovery curve for test C48 is shown in Figure 9, together with the balanced grade-recovery curve obtained from locked-cycle test 52. At a concentrate grade of 33.1% Cu, the open circuit test C48 would have yielded a recovery of 74.9%; however, the balanced locked-cycle test achieved 84.9%, representing a positive shift of +10.0%.

By moving along the locked-cycle grade-recovery curve to a reduced concentrate grade of 25% Cu, it is projected that the circuit will yield a recovery of 85.8% Cu. This correlates well with the 2023 FSU average locked-cycle test results for the Copperwood Main Zone of 85.8% recovery at 25.1% Cu grade. These results

underscore the robustness of the redesigned flowsheet and its ability to achieve comparable outcomes to the 2023 FSU, but at substantially lower operating costs.

Positive Pilot-scale Results for Ultrafine Flotation Technology

Ultrafine flotation technology plays a critical role in recovering very fine particles-typically those smaller than 20 µm-that are often lost in conventional flotation circuits. QEMSCAN analysis of Copperwood ore confirmed that the liberation size of the copper mineralization is sub-20 µm, supporting the historical process design which incorporated a regrind P80 of 14 µm.

The primary objective of evaluating ultrafine flotation at Copperwood is to enhance the grade-recovery curve, a key driver of project economics. In addition, this technology offers potential secondary benefits, including reduced processing plant footprint and a lower environmental impact, aligning with the project's sustainability objectives.

Figure 9: Shift in grade-recovery curve from open circuit to closed circuit locked cycle test

The Jameson Cell, developed by Glencore Technology, was selected for pilot testing. It addresses many of the design and performance limitations of conventional flotation and column cells. With over 500 installations worldwide-including more than 140 in copper circuits-the Jameson Cell is a proven solution, extensively documented in technical literature and industrial case studies.

Following the confirmation of the MF2 circuit configuration and optimized reagent regime through bench-scale testing, the program advanced to the pilot application of ultrafine flotation using a Jameson L150 laboratory unit at Base Met Labs.

Pilot-scale flotation tests, using 40kg batches from the composite sample, were conducted on both the primary and secondary rougher applications, as well as the open circuit cleaner application. Prior to each test, a representative sample was extracted from the conditioning tank post-reagent conditioning and subjected to a three-stage dilution test-a standard Glencore Technology method using a D12 Denver bench-top flotation cell. This approach is designed to mimic Jameson Cell conditions and allows for direct comparison of performance and scale-up parameters.

The mass pull versus recovery curve from a primary rougher test, together with a grade versus recovery curve from the corresponding dilution test, is plotted alongside the benchmark MF2 Test R23R in Figure 10. These results demonstrated a distinct and favorable shift in flotation performance with the use of a Jameson Cell, indicating improved kinetics and recovery potential and affirming the value of ultrafine flotation technology in the Copperwood flowsheet.

Table 4 presents a comparative analysis of bench-scale flotation performance achieved during the 2025 testing campaign using conventional flotation cells, versus a configuration utilizing Jameson L150 cells in both the primary and secondary rougher applications. In both scenario's, the test work employed the revised reagent scheme (as detailed in Table 2) and the MF2 flowsheet configuration (see Figure 4 for stream references). Key observations from the data include:

- The 95% confidence interval for the Rougher Tail mass fraction (stream C) in the conventional cell baseline is 18.4% to 23.7% with a mean of 21.0%. The Jameson cell configuration yielded a significantly higher rougher tail mass fraction of 32.0%, a statistically significant difference. This suggests improved selectivity and reduced entrainment in the rougher circuit using ultrafine flotation technology.

Figure 10 is available at
<https://www.globenewswire.com/NewsRoom/AttachmentNg/c079bed4-78fd-4d66-9571-8839fe566499>

Figure 10: Comparison of L150 Jameson cell mass pull versus recovery curve with 3-stage dilution and 2025

baseline rougher tests.

- The copper grade in the conventional Rougher Tail (stream C) had a 95% confidence interval of 0.35% to 0.51% Cu, with a mean of 0.43% Cu. The Jameson cell circuit achieved a lower tailings grade of 0.30% Cu, indicating a statistically significant improvement in rougher recovery.
- At a comparable rougher copper recovery of 90%, the Jameson L150 cell produced a rougher concentrate grade of 5.4% Cu, compared to the baseline range of 4.3% to 4.7% Cu (95% confidence interval). This higher concentrate grade is statistically significant and confirms that the ultrafine flotation technology delivers a favorable shift in the rougher grade-recovery curve.

Table 4: Jameson L150 and bench test comparison on rougher performance (see Figure 4 for circuit configuration)

Test ID	Type	Avg Calc Feed [A]		Slime Tail [B]		Recovery %Cu	Rougher %Cu	Mass
		% Cu		Mass Grade	%Cu			
BL1847-22R	Bench Rougher	2.25		30.4	0.33	4.5		24.65
BL1847-23	Bench Rougher	2.25		34.3	0.35	5.3		23.87
BL1847-34R	Bench Rougher-Cleaner	2.25		35.1	0.43	6.7		19.34
BL1847-37	Bench Rougher-Cleaner	2.25		36.0	0.39	6.2		18.94
BL1847-36	Bench Rougher-Cleaner	2.25		32.8	0.37	5.4		19.71
BL1847-39	Bench Rougher-Cleaner	2.25		33.6	0.46	6.9		19.69
Bench-test baseline performance		2.25		33.7	0.39	5.8		21.03
BL1847-38	Jamo L150	2.25		30.7	0.42	5.7		32.01

Encouraged by the improved rougher performance, additional Jameson L150 pilot plant tests were conducted under the MF2 circuit configuration, incorporating both the de-slime circuit and revised reagent regime. The combined primary and secondary rougher concentrates were milled in a pilot ISAMill to a P80 of 15 µm before being fed into an L150 Jameson cell operating in open-circuit primary cleaner duty.

The grade-recovery curve for this "Jamo 53" test is shown in Figure 11, alongside the open-circuit and locked-cycle test results presented in Figure 9 for comparison. The results clearly demonstrate that the L150 open-circuit test outperformed the C48 baseline. To predict closed-circuit performance, all pilot plant, three-stage dilution, and locked-cycle test results were provided to Glencore Technologies, who incorporated the data into a closed-circuit simulation model.

Figure 11: Conventional vs Jameson cell performance in open and closed circuit

The modeled grade-recovery curve for the Jameson cleaner circuit (Figure 11) indicates that at a concentrate grade of 25% Cu, the circuit is expected to deliver recoveries of up to 87.6%. Importantly, because the simulation is based on test work completed at an accredited laboratory, Glencore Technologies is prepared to offer a process guarantee for this performance.

Quality Control:

All metallurgical test work was carried out at Base Metallurgical Laboratories Ltd. (Base Met Labs) in Kamloops, British Columbia. The laboratory maintains rigorous internal quality control protocols to ensure the accuracy and reliability of reported data. Base Met Labs participates in the Intertek Global Proficiency Program, conducting regular internal proficiency testing as part of its quality assurance procedures.

Qualified Person Statement:

The information in this news release relating to metallurgical test work results is based on, and fairly reflects,

information reviewed by Dr. Aghil Ojaghi, P.Eng., Senior Process Engineer at DRA for the Copperwood Project and independent from the Company. Dr. Ojaghi is a Qualified Person under National Instrument 43-101 - Standard of Disclosure for Mineral Projects. He is a professional engineer with relevant experience in metallurgical testing and process plant design and has reviewed and approved the technical content as it pertains to his area of responsibility. Dr. Ojaghi consents to the inclusion of this information in the form and context in which it appears.

The overall technical content of this news release has been reviewed and approved by Dr. Wynand van Dyk, a Qualified Person as defined by NI 43-101. Dr van Dyk is employed as Project Director by Copperwood Resources Inc, a wholly owned subsidiary of Highland Copper.

About Highland Copper Company:

Highland Copper Company Inc. is a Canadian company focused on exploring and developing copper projects in the Upper Peninsula of Michigan, U.S.A. The Company owns the Copperwood deposit through long-term mineral leases and 34% of the White Pine North project through a joint venture with Kinterra Copper USA LLC. The Company also owns surface rights securing access to the Copperwood deposit and providing space for infrastructure at Copperwood as required. The Company has 736,363,619 common shares issued and outstanding. Its common shares are listed on the TSX Venture Exchange under the symbol "HI" and trade on the OTCQB Venture Market under symbol "HDRSF".

More information about the Company is available on the Company's website at www.highlandcopper.com and on SEDAR+ at www.sedarplus.com.

Cautionary Note Regarding Forward-Looking Information:

This news release contains "forward-looking statements" and "forward-looking information" (collectively "forward-looking statements") within the meaning of applicable Canadian securities legislation. These statements include, without limitation, statements with respect to: the potential to advance engineering studies and project optimization at Copperwood, and the anticipated benefits thereof; the completion of lock-cycle variability testing in Q4 2025; completion of process design criteria; and the determination to make a construction decision in 2026. The forward-looking statements are subject to a number of assumptions, including those set out in the technical reports entitled "Feasibility Study Update Copperwood Project Michigan, USA" and the Company's annual information form for the year ended June 30, 2024 (the "AIF"). These underlying assumptions may prove to be incorrect. Important factors that could materially impact the Company's expectations include: the results of metallurgical testing in laboratory environments may not be repeated in industrial settings; reagent prices are subject to fluctuations, which may reduce or eliminate expected reagent cost savings; new flow designs may change capital cost requirements, which have not yet been estimated; completion of remaining work programs may not lead to a construction decision; changes in project parameters as plans continue to be refined; availability of services, materials and skilled labour to complete work programs, testing and drilling; effects of regulation by governmental agencies; the fact that permit extensions, renewals and amendments are subject to regulatory approvals, which may be conditioned, delayed or denied; advancement to a construction decision at Copperwood is subject to additional studies, for which the Company will require additional funds, which may not be available on a timely basis and accordingly could delay a construction decision; the Company will be required to repay the loan facility from Kinterra in July, 2026, or will have its interest at White Pine diluted; unexpected cost increases, which could include significant increases in estimated capital and operating costs and the effects of inflation; fluctuations in metal prices and currency exchange rates; general market and industry conditions, the results of baseline studies and test work may result in unforeseen issues which could delay or hamper advancement of the projects, and the other risks set out in the Company's public disclosure documents, including the AIF, filed on SEDAR+. Although the Company believes that the assumptions and factors used in preparing the forward-looking statements in this news release are reasonable, undue reliance should not be placed on forward looking statements. All forward-looking statements in this press release are based on information available to the Company as of the date hereof, and the Company undertakes no obligation to update forward-looking statements except as required by law.

Neither the TSX Venture Exchange nor its Regulation Services Provider (as that term is defined in the policies of the TSX Venture Exchange) accepts responsibility for the adequacy or accuracy of this release.

For further information or media requests, please contact:

Barry O'Shea, CEO
Email: info@highlandcopper.com
Website: www.highlandcopper.com

¹ See "Feasibility Study Update Copperwood Project Michigan, USA" with an Effective Date of March 6, 2023, prepared for the Company by G Mining Services Inc. available under the Company's profile at www.sedarplus.com

² The SGS report entitled "Optimization Flotation Testwork on Material from the Copperwood Deposit", Project 16256-002-Final Report, August 28, 2018 forms the baseline used in the previous process design, and is discussed in the 2023 Feasibility Study (FSU) for the Copperwood project.

Photos accompanying this announcement are available at

<https://www.globenewswire.com/NewsRoom/AttachmentNg/bc70f093-965d-48ea-b832-2c1c4582a939>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/9eccc611-1235-4129-9ebc-0ff74dc52603>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/fc5deb6f-274a-4cd6-87ef-c7d7244744a2>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/443eeef-7ef6-44e1-993f-b469bbe152c5>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/1f0f73f9-2618-4db2-8b76-fcd12c46ece1>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/cc9f281a-de57-4730-82a8-f80e88afda1b>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/63b88a59-023a-4974-a1d5-156f431d5ffe>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/fe24c0f6-2981-4dde-a573-e798989b2794>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/c9e8b98a-528e-40d1-a9b3-0aca7c385292>

<https://www.globenewswire.com/NewsRoom/AttachmentNg/f94b927b-f373-46f7-bebc-50e7cee1033e>

Dieser Artikel stammt von Minenportal.de

Die URL für diesen Artikel lautet:

<https://www.minenportal.de/artikel/574919--Highland-Copper-Announces-Updated-Process-Plant-Flow-Sheet-Demonstrating-Increased-Copper-Recoveries-of>

Für den Inhalt des Beitrages ist allein der Autor verantwortlich bzw. die aufgeführte Quelle. Bild- oder Filmrechte liegen beim Autor/Quelle bzw. bei der vom ihm benannten Quelle. Bei Übersetzungen können Fehler nicht ausgeschlossen werden. Der vertretene Standpunkt eines Autors spiegelt generell nicht die Meinung des Webseiten-Betreibers wieder. Mittels der Veröffentlichung will dieser lediglich ein pluralistisches Meinungsbild darstellen. Direkte oder indirekte Aussagen in einem Beitrag stellen keinerlei Aufforderung zum Kauf/-Verkauf von Wertpapieren dar. Wir wehren uns gegen jede Form von Hass, Diskriminierung und Verletzung der Menschenwürde. Beachten Sie bitte auch unsere [AGB/Disclaimer!](#)

Die Reproduktion, Modifikation oder Verwendung der Inhalte ganz oder teilweise ohne schriftliche Genehmigung ist untersagt!
Alle Angaben ohne Gewähr! Copyright © by Minenportal.de 2007-2025. Es gelten unsere [AGB](#) und [Datenschutzrichtlinien](#).